

# Conplast Crystalline

**Integral waterproofing admixture based on crystalline formation to produce water tight concrete.**

## Uses

Conplast Crystalline is an integral waterproofing admixture to produce watertight concrete. The active chemical in Conplast Crystalline react with moisture available in concrete to produce non soluble crystalline formation throughout the pores of capillary tracks thus making concrete permanently sealed against water penetration from any direction.

Conplast Crystalline is developed to use in;

- All types of concrete foundation below ground
- Water reservoir
- Tunnel Concreting
- Retaining walls and subways
- Deck slab - Bridges, plinth and intermediate slab used for car parking
- Water tank and Swimming pools
- Precast unit

## Advantages

- Easy to use, require only mixing with concrete.
- Integral waterproofing system.
- Crack filling property with time up to 0.4 mm width
- Exhibits good resistance to hydrostatic water pressure both surface. (up to 14 bar)
- Compatible with our full range of water reducing admixture.
- More effective due to formation of crystalline in tiny capillaries.
- Reduce Shrinkage and Creep
- Increase Durability

## Description

Conplast Crystalline is a powder form with perfect blend of Portland cement with other ingredients. Crystalline chemicals react with water in concrete to form crystals structure in the tiny capillaries. These insoluble crystals structure that clogs.

## Technical Support

Fosroc provides technical advisory service for on-site assistance and guidance on mix design, optimum dosage evaluation of trials.

## Properties

<b>Appearance</b>	: Grey powder
<b>Bulk density</b>	: 1400 Kg/m <sup>3</sup>
<b>Workability Retention</b>	: To be adjusted using water reducing and retarding admixture as required..
<b>Compatible with cement</b>	: Can be used with all cements including pozzolonic cements.
<b>Permeability to water</b>	: Has very low permeability compared to control concrete
<b>Setting time</b>	Confirm to IS 2645-2003 for initial and final.

## Dosage

The optimum dosage of Conplast Crystalline to meet specific requirement should always be determined by conducting laboratory and batch trials. However the normal dosage ranges between 1 to 2 percent by weight of total cement or binder content.

## Instruction for Use

### Compatibility

Conplast Crystalline is compatible with our water reducing admixture when used in the same concrete mix, but should be added to the mix separately. The resultant properties of mixes containing more than one admixture should be assessed by the trial mix procedure recommended on this data sheet.

Conplast Crystalline is suitable for use with all types of Portland cements, SRC cements and cement replacement materials such as PFA, GGBFS and microsilica.

### Dispensing

The optimized quantity of Conplast Crystalline must be added directly into the wet concrete at the time of mixing. For Ready Mix Plants, Conplast Crystalline can be added at site and mixed to ensure uniform distribution throughout concrete mix.

# Conplast Crystalline

In order to obtain uniform distribution, each kg of Conplast Crystalline must be mixed with 0.5 litre of water to form thin slurry form. Then Conplast Crystalline slurry shall be dispensed into transit mixer and mixed well before pumping or placing. Suggest not adding Conplast Crystalline powder directly into concrete. Make sure that water used for preparing slurry must be deducted from concrete total water to ensure designed water cement ratio. Consult with Fosroc technical department for additional information.

## Curing

As with all structural concrete, good curing practice should be maintained, particularly in situations where an overdose has occurred. Water spray, wet hessian or Concure spray applied curing membrane should be used.

## Packing

Conplast Crystalline	: 15 kg
----------------------	---------

## Storage

### Shelf Life

Conplast Crystalline has a minimum shelf life of 6 months provided the temperature is kept within range of 5°C & 50°C

## Precautions

### Health and safety

Conplast Crystalline is alkaline and should not be swallowed or allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles. In case of contact with the skin, wash immediately with soap and water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting. For further information consult the Safety Data Sheet available for this product.

## Fire

Conplast Crystalline is non-flammable.

## Cleaning and disposal

Spillages of Conplast Crystalline should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Hose down remnants with large quantities of water. The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance

## Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office



### Önemli Hatırlatma

Fosroc ürünleri malzeme ve üretim kusurlarına karşı garantili olup Fosroc Mal ve Hizmet Tedarik Koşullarına uygun olarak satılır. Tüm Fosroc bilgi föyleri düzenli olarak güncellenmektedir. En son versiyona sahip olmak kullanıcının sorumluluğundadır

## FOSROC İDEA YAPI

### KİMYASALLARI

Aydınevler Mah.Sanayi Cad.  
Demirtaş Plaza No:13 D:7-8  
Maltepe İstanbul / TÜRKİYE

[www.fosroc.com](http://www.fosroc.com)

Telefon :  
+90 216 463 69 63

Faks :  
+90 216 463 67 76

email:  
EnquiryTurkey@Fosroc.com

TR/8001/20/A